

## Flocking with 9888 Vinyl

9888 Vinyl is a polyvinyl alcohol stabilised, vinyl acetate / ethylene copolymer. 9888 Vinyl is a medium viscosity adhesive, ideal for use on high speed packaging equipment, film lamination or in filter manufacture. 9888 is ideal for use on products where the air moisture content is high or where substrates may be difficult to bond e.g. varnished board, vinyl. It is characterised by its high wet grab, fast setting speed, excellent adhesion to low surface energy substrates and good heat and moisture resistance. 9888 shows excellent adhesion to plastic films and is therefore and is therefore suitable for polyester, polystyrene, PVC and coated cellophanes. In addition to its adhesive properties, 9888 has excellent machine running properties, ensuring it is ideal for high speed equipment. The adhesion to the substrate is considerably improved after the substrate has been wiped with a solvent, such as acetone. The solvent not only acts a de-greaser, but it also works to key the substrate, enabling a stronger bond with the adhesive. 9888 Vinyl is water resistant to cool and warm waters. In its cured state it is a flexible translucent film.

### Materials 9888 Vinyl is suitable for

- Varnished boards
- Vinyl
- Polyester
- Polystyrene
- PVC
- Coated cellophanes

### Preparation of the substrate

The substrate must be clean, dry and grease-free before the adhesive is applied. It is important that the adhesive coating does not get absorbed by the surface of the substrate, therefore, with porous substrates (e.g. wood, chipboard, etc), a primer (such as PVA glue) may have to be used prior to the adhesive. A thick layer of adhesive must be applied (approximately 1/10 of the length of the flock fibre), so that the flock can adhere adequately to the substrate.

The adhesion to the substrate is considerably improved after the substrate has been wiped with a solvent, such as acetone. The solvent not only acts a de-greaser, but it also works to key the substrate, enabling a stronger bond with the adhesive.

### Method of Application

There are various ways to apply the adhesive; any way that you can apply paint to a surface is also a possible way to apply the adhesive. Any of the following methods can be used (although some will be more successful after the viscosity of the adhesive has been reduced).

- Paint Brush
- Paint Roller
- Spray Gun

The adhesive must not be applied to any part of the substrate that does not require flocking. Those areas should be covered with a mask or sealed off with masking tape.

### Curing Times

Air Temperature	Curing Time	
	Working Cure	Full Cure
°C	hrs	hrs
°C	hrs	hrs

### Using Pigments

Pigments can be added to the adhesive, in order to achieve a seamless finish, where the substrate is a markedly different colour to the flock being used. In addition, if the substrate comprises more than one colour, adding pigment to the adhesive will prime the substrate, giving a uniform appearance. The adhesive is matched to the flock in colour. This also compensates for areas with a slightly lower flock density (e.g. in interior corners).

When applying a dark flock onto a bright substrate a few percents of pigment added are quite sufficient. At least 10% of white pigment has to be added to the adhesive for white flocking onto dark surfaces. When you are flocking a lighter coloured flock onto a darker coloured substrate (e.g. yellow flock onto a blue substrate) it will be necessary to add white pigment, as well as pigment matching the colour of the flock, to the adhesive in order to attain the appropriate finish.

### Reducing the viscosity of 9888 Vinyl

9888 Vinyl can be used straight from the container, it can also be diluted with water. By thinning down the adhesive, you increase the range of possible uses, for example, priming a substrate or spray application. The adhesive can be thinned down by ?%.

### Storage

9888 Vinyl should be stored in well sealed containers (to prevent the evaporation of water and the formation of a skin on the surface) away from heat, direct sunlight and frost, at temperatures between 5°C and 25°C for not more than 6 months. Higher temperatures will affect quality and cause the formation of crusts and skins, especially if the containers are not tightly closed or subjected to direct sunlight for long periods.

### Cleaning

To clean skin, equipment, etc whilst the adhesive is still wet, use water. Once the adhesive has been allowed to dry it is necessary to use ?

### Health & Safety

9888 Vinyl is not classified as harmful if handled with normal care. However, it should not be ingested and care should be taken to avoid contact with skin and eyes. Splashes should be thoroughly rinsed with water.

Spillages can be absorbed with sawdust or other suitable material and small quantities may be washed away with water according to Local Authority Regulations.

The adhesive is water-based and is, therefore, non-flammable.



Suppliers of....

Flocking equipment

Flock

Adhesives

Adhesive Applicators

Pigments

Protective Clothing

### DCA Electrostatics

Campbell Coutts Ltd  
Unit 7,  
Tower Industrial Estate,  
Tower Lane,  
Eastleigh,  
Hampshire,  
England,  
SO50 6NZ  
[sales@flocking.biz](mailto:sales@flocking.biz)  
[www.flocking.biz](http://www.flocking.biz)  
tel: +44(0) 23 80613700  
fax: +44(0) 23 80613355